

IMPREGNATED GRAPHITE

TYPE	Impregnated graphite material	Bulk density (g/cm ³)	Bending Strength (MPa)	Compressive Strength (MPa)	C.T.E (100-600) °C (10-6/°C)	HSD
M126G	Silver (G)	2.8	65	190	/	70
M126P	Copper (P)	2.2	70	210	6.8	70
M201P		2.2	70	190	6	65
M254P		2.4	45	110	6	50
M252A	Aluminium alloy (A)	2	60	120	7.3	40
M134B	Babbit metal (B)	2.4	65	150	6	60
M201B		2.5	50	130	5.3	55
M254B		2.6	40	70	5.2	40
M126D	Antimony (D)	2.8	65	195	7	110
M126K	Furan resin (K)	1.8	60	165	6	80
M252K	Phenolic resin(K)	1.85	80	195	7	105

*□The above data should be regarded as general information, not guaranteed specification limits.