

Technical Data Sheet

Item Name: Expandable Graphite

Date: April 24, 2024

No.	Analysis Item	Unit	50 Mesh	80 Mesh	100 Mesh	140 Mesh
1	Particle Size(65% on)	Mesh	50	80	100	140
2	The Standard Initial Expansion Temperature	°C	220	220	220	220
3	The Typical Expansion Volume at 600°C	cm ³ /g	200	200	200	200
4	The Purity	%	≥93	≥93	≥93	≥93